



## PRODUCT SPECIFICATION

### EPDM Scrim

Issued: 2010-01-13  
Revision of: 1997-09-22

---

PHYSICAL PROPERTIES	UNIT	REQUIREMENTS	TYPICAL VALUE	TEST METHODS
Hardness	°IRH	70 ± 5	69	ISO 48
Tensile strength	N/50mm	500	560	EN 12311-2
Elongation at break (rubber)	%	>200	350	EN 12311-2
Foldability at low temperature	°C	<-30	-40	EN 495-5

#### SealEco

**Tel:** +46 (0) 370 481 00  
**Fax:** +46 (0) 370 485 00  
**Email:** info@sealeco.com  
**Internet:** www.sealeco.com

**Office Address:** Kävsjövägen 38,  
SE-331 35 Värnamo, Sweden  
**Post Address:** Box 514,  
SE-331 25 Värnamo, Sweden  
**Org. No.** 556739-6980